

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : B01J	A2	(11) International Publication Number: WO 92/15394 (43) International Publication Date: 17 September 1992 (17.09.92)
(21) International Application Number: PCT/US92/01626 (22) International Filing Date: 28 February 1992 (28.02.92) (30) Priority data: 662,122 28 February 1991 (28.02.91) US 820,057 16 January 1992 (16.01.92) US (71) Applicant: MINNESOTA MINING AND MANUFACTURING COMPANY [US/US]; 3M Center, P.O. Box 33427, Saint Paul, MN 55133 (US). (72) Inventors: MOON, John, D. ; ZIEGLER, Louis, A. ; VESLEY, George, F. ; MEHNER, Robert, C. ; EDBERG, Mark, S. ; ANDERSON, Robert, D. ; P.O. Box 33427, Saint Paul, MN 55133 (US).		(74) Agents: SPRAGUE, Robert, W. et al.; Office of Intellectual Property Counsel, Minnesota Mining and Manufacturing Company, P.O. Box 33427, Saint Paul, MN 55133 (US). (81) Designated States: AT (European patent), AU, BE (European patent), BR, CA, CH (European patent), DE (European patent), DK (European patent), ES (European patent), FR (European patent), GB (European patent), GR (European patent), IT (European patent), JP, KR, LU (European patent), MC (European patent), NL (European patent), SE (European patent). Published <i>Without international search report and to be republished upon receipt of that report.</i>
(54) Title: MULTI-STAGE IRRADIATION PROCESS FOR PRODUCTION OF ACRYLIC BASED COMPOSITIONS AND COMPOSITIONS MADE THEREBY (57) Abstract Disclosed is a novel, multi-stage irradiation process for the production of acrylic-based compositions such as adhesives or pressure-sensitive adhesive tapes. The first irradiation step or stage employs electromagnetic radiation at a relatively low average intensity (i.e., 0.1 to 20 mW/cm ²) to effect a relatively low extent of monomer conversion, and the subsequent step employs electromagnetic radiation at a relatively higher average intensity (i.e., greater than 20 mW/cm ²) to complete the photopolymerization. Also disclosed are acrylic-based psa tape materials made by the novel process.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FI	Finland	MI	Mali
AU	Australia	FR	France	MN	Mongolia
BB	Barbados	GA	Gabon	MR	Mauritania
BE	Belgium	GB	United Kingdom	MW	Malawi
BF	Burkina Faso	GN	Guinea	NI	Netherlands
BG	Bulgaria	GR	Greece	NO	Norway
BJ	Benin	HU	Hungary	PL	Poland
BR	Brazil	IE	Ireland	RO	Romania
CA	Canada	IT	Italy	RU	Russian Federation
CF	Central African Republic	JP	Japan	SD	Sudan
CG	Congo	KP	Democratic People's Republic of Korea	SE	Sweden
CH	Switzerland	KR	Republic of Korea	SN	Senegal
CI	Côte d'Ivoire	LI	Liechtenstein	SU	Soviet Union
CM	Cameroon	LK	Sri Lanka	TD	Chad
CS	Czechoslovakia	LU	Luxembourg	TG	Togo
DE	Germany	MC	Monaco	US	United States of America
DK	Denmark	MG	Madagascar		
ES	Spain				

- 1 -

MULTI-STAGE IRRADIATION PROCESS FOR
PRODUCTION OF ACRYLIC BASED COMPOSITIONS
AND COMPOSITIONS MADE THEREBY

5

Field of the Invention

This invention relates to a process for the production of adhesives and more particularly, it relates to a multi-stage irradiation process for the production of acrylic-based adhesives, especially pressure-sensitive adhesive tapes. It also relates to acrylic-based adhesives and tapes made by the novel processes of this invention.

15

Background of the Invention

It is known in the literature and in the industry that there are at least four different feasible methods for the production of acrylic-based pressure-sensitive adhesive (hereinafter "psa") tapes. These known methods include solution polymerization, emulsion polymerization, irradiation by high energy particulate matter (e.g., electron beams or gamma rays), and ultraviolet light (hereinafter "UV") photopolymerization. As explained below, however, there are disadvantages and/or limitations incurred with the use of each known process.

When utilizing psa's made by solution polymerization, elaborate drying ovens with massive exhaust ducts and high temperatures are required to carry away the volatile solvents after coating. Furthermore, to prevent the solvents from being vented to the atmosphere (with resulting pollution and solvent loss), expensive solvent recovery equipment has been necessary. Safety hazards in such operations are also severe, as the solvents are extremely flammable and precautions must be taken to avoid explosive mixtures

- 2 -

in the oven and exhaust systems. A further limitation of the solvent based systems is the limit on the thickness of the coatings which can be deposited in one trip or pass through the coater. Thus, with coatings
5 above about 5 mils, multiple coating layers must be deposited in successive trips through the coater to avoid blistering of the coating due to solvent evaporation.

While emulsion polymerization has eliminated the
10 problems associated with the handling and evaporation of flammable solvents, the heat of vaporization must be supplied to remove the water from the coating and essentially the same equipment must be employed. Though higher solids coatings are possible, the higher
15 heat of vaporization of water as compared to organic solvents offsets this benefit and about the same total energy for drying is required. Drying times are relatively long, thus limiting production. One of the most serious limitations of the emulsion polymerization
20 process is the water sensitivity of the resulting polymers (caused by the emulsifying agent which is carried along in the process and becomes part of the final polymer). A further limitation of this process is that highly polar monomers, which are water
25 miscible, are difficult to incorporate into the copolymer during polymerization and considerable homopolymerization of such monomers can occur in the aqueous phase.

Various attempts have been made to avoid the
30 difficulties of the solution and emulsion polymerization processes. However, those have thus far resulted either in processing difficulties of their own or have produced polymers in which a proper balance between compliance and cohesive strength is very
35 difficult to control.

More recently, development work has been done with polymerization processes which employ either

- 3 -

ultraviolet light or electron beams. One patent which stresses electron beam curing is U.S. Pat. No.

3,897,295, in which the composition subject to the electron beam includes an acrylate monomer selected
5 from a particular specified group, and a homopolymer or copolymer of a substance or substances selected from the same group. The polymer is dissolved in the monomer and the monomer is ultimately polymerized to bind the adhesive together.

10 The disadvantage of utilizing polymerization processes involving an electron beam, though, is that, generally, it is a rather indiscriminate polymerization process. In polymerization processes utilizing an electron beam, the particulate bombardment of the free-
15 radically polymerizable monomers cannot be precisely controlled, with the result being chain scission of the developing polymer and an inability to control its molecular weight and crosslink density to the most desired range.

20 In order to avoid the above-discussed disadvantages incurred with the use of an electron beam, some have chosen to utilize a one step or stage low-intensity (e.g., 0.1 to 7 mW/cm²) UV photopolymerization process. See, for example, U.S.
25 Pat. No. 4,181,752. Whereas the use of relatively low intensity UV light is very desirable for building higher molecular weight acrylic psa's with good performance properties, an increase in the speed of the photopolymerization process would be desirable.

30 However, if one attempts to increase the speed of the low intensity UV light-based process by increasing the amount of the photoinitiator employed (e.g., benzoin ethers, benzil ketals, etc.), then undesirable lower molecular weight polymers will be obtained.

35 Furthermore, for thick adhesives an uneven polymerization from the front surface to the back surface of an irradiated adhesive composition occurs

- 4 -

due to the uneven light absorption by the photopolymerization initiator resulting in a differential performance of the final psa product.

JP 63-214,484 discloses a two-stage photopolymerization process for preparing acrylic psa's. The first stage involves low intensity UV light (i.e., 0.1 to 30 mW/cm²) and the second stage involves higher intensity UV light than that involved in the first stage. The publication discloses that at least 90 weight % of the vinyl group monomer be reacted in the first stage, although a comparative example mentions 75 weight % conversion.

In view of the foregoing discussed disadvantages and limitations that exist with the use of conventional polymerization processes, improvements are continuously desired and sought by those within the industry. It was against this background that an improved polymerization or irradiation process for producing acrylic-based adhesives, and in particular acrylic-based psa tapes was sought.

Summary of the Invention

By the present invention, we have now discovered that an increase in the speed of the photopolymerization process for the production of acrylic-based compositions such as adhesives and acrylic-based psa tapes with acceptable product properties can be achieved by utilizing a multi-stage (as opposed to the conventional one-step) irradiation process, the first stage employing electromagnetic radiation at a relatively low intensity to effect a relatively low extent of monomer conversion, and the subsequent stage employing electromagnetic radiation at a relatively higher intensity to substantially complete the photopolymerization.

Accordingly, in one embodiment of the present invention, the inventive multi-stage irradiation

- 5 -

process for the production of an acrylic-based composition comprises the sequential steps of:

- (a) forming a monomeric mixture or partially prepolymerized syrup comprising:
 - 5 (i) about 50-100 parts by weight of at least one acrylic acid ester of an alkyl alcohol, the alcohol containing from 1 to 14 carbon atoms;
 - (ii) about 0-50 parts by weight of at least
10 one copolymerizable monomer; and
 - (iii) a photoinitiator;
- (b) irradiating the resulting monomeric mixture or syrup with electromagnetic radiation of
15 from about 280 to 500 nanometer wavelength and from .01 to 20 mW/cm² average light intensity to effect conversion of about 5-70 weight % of the monomeric mixture or partially prepolymerized syrup to an acrylic copolymer; and
- 20 (c) thereafter, irradiating the acrylic copolymer resulting from step (b) with electromagnetic radiation of from about 280 to 500 nm wavelength and having an average light
25 intensity of greater than 20 mW/cm² to at least substantially complete the photopolymerization reaction of the acrylic copolymer.

In another embodiment of the present invention, the inventive multi-stage irradiation process for the
30 production of an acrylic-based composition comprises the sequential steps of:

- (a) forming a monomeric mixture or partially prepolymerized syrup comprising:
 - 35 (i) about 50-100 parts by weight of at least one acrylic acid ester of an alkyl

- 6 -

- alcohol, said alcohol containing from 1 to 14 carbon atoms;
- (ii) about 0-50 parts by weight of at least one copolymerizable monomer; and
- 5 (iii) a photoinitiator;
- (b) irradiating the resulting monomeric mixture or partially prepolymerized syrup in a substantially inert environment with electromagnetic radiation of from about 280 to 500 nanometers wavelength and from .01 to 10 20 milliwatts per centimeter squared (mW/cm^2) average light intensity to effect conversion of from about 5 to 85 or 90 weight % of said monomeric mixture or partially prepolymerized 15 syrup to an acrylic copolymer; and
- (c) thereafter and while maintaining the substantially inert environment, further irradiating the resulting acrylic copolymer 20 resulting from step (b) with electromagnetic radiation of from about 280 to 500 nm wavelength and having an average light intensity of greater than $20 \text{ mW}/\text{cm}^2$ to at least substantially complete the 25 polymerization reaction of said acrylic copolymer.

In yet another embodiment of the present invention, pressure-sensitive adhesive tapes are produced by coating the monomeric mixture or prepolymerized syrup onto a substrate and thereafter, 30 irradiating the coated substrate as per steps (b) and (c) of the foregoing disclosed processes.

In still other embodiments of the present invention, acrylic-based compositions such as adhesives and psa tapes are provided which are produced by the 35 foregoing disclosed, inventive processes.

- 7 -

In a preferred embodiment, Stage 1 (or step (b) above) of the processes effects conversion of about 5 or 10 to 50 weight % of the monomeric mixture. Even more preferably the extent of conversion effected in Stage 1 is about 10-40 weight %. Even more preferably yet, the extent of conversion effected in Stage 1 is about 20-40 weight %.

The inventive multi-stage irradiation process does not have the limitations and drawbacks discussed earlier herein associated with conventional polymerization processes. The fact that the inventive process employs sequential irradiation steps or stages, one involving exposure to electromagnetic radiation at low average intensity to effect a relatively low extent of monomer conversion and a subsequent stage or step involving exposure to electromagnetic radiation at a higher average intensity to complete the photopolymerization, is significant because the process is not only highly efficient, but it also produces an acrylic-based psa product having excellent properties, e.g. high shear strengths and adhesion values, as well as adhesive products and other articles which are not pressure-sensitive at room temperature.

Other aspects, advantages, and benefits of the present invention are apparent from the detailed disclosure, examples, and claims.

Detailed Description of the Invention

In the first step of the inventive process, a photopolymerizable monomeric mixture or partially prepolymerized syrup is made by mixing together the components described below.

The photopolymerizable monomeric mixture comprises about 50-100 parts by weight, preferably about 60-98 parts by weight, of at least one acrylic acid ester of an alkyl alcohol (preferably a non-tertiary alcohol), the alcohol containing from 1 to 14 (preferably 4 to

- 8 -

14) carbon atoms. Included within this class of monomers are, for example, isooctyl acrylate, isononyl acrylate, 2-ethyl-hexyl acrylate, decyl acrylate, dodecyl acrylate, n-butyl acrylate, methyl acrylate, and hexyl acrylate. Preferred monomers include isooctyl acrylate, isononyl acrylate, and butyl acrylate, and 2-ethyl-hexyl acrylate.

The acrylic acid ester ("acrylate") is polymerized with about 0-50 parts by weight, preferably about 2-40 parts by weight, of at least one copolymerizable monomer which is typically an ethylenically unsaturated reinforcing comonomer such as, for example, acrylic acid, methacrylic acid, acrylamide, acrylonitrile, methacrylonitrile, N-substituted acrylamides, hydroxy acrylates, N-vinyl lactam, N-vinyl pyrrolidone, maleic anhydride, isobornyl acrylate, and itaconic acid.

In a preferred embodiment of the present invention, the viscosity of the monomer mixture is increased to a more desirable level so that it can be handled more conveniently during the coating process. In order to increase the viscosities to a more desirable level, the monomer mixtures can be partially prepolymerized. The prepolymerization can be accomplished by exposure to electromagnetic radiation (such as UV light) or by thermal polymerization. Other methods of increasing the viscosity of the monomer mixture are also available, however, such as the addition of viscosity modifying agents such as high molecular weight polymers or thixotropic agents such as colloidal silicas, etc. A syrup is a monomeric mixture thickened to a coatable viscosity.

If a psa tape is to be made, the monomeric mixture or prepolymerized syrup of a viscosity of, for example, about 2500 to 4000 centipoises can be coated onto any suitable substrate (e.g., backing or liner) including, for example, films (transparent and non-transparent),

- 9 -

cloths, papers, non-woven fibrous constructions, metal foils, and aligned filaments.

Afterwards, the monomeric mixture or partially prepolymerized syrup is photopolymerized in Stage 1 by
5 irradiating the same with electromagnetic radiation of 280 to 500 nanometer wavelength and .01 to 20 mW/cm² average light intensity to effect about 5 to 70 or 85 weight % conversion of the monomeric mixture or prepolymerized syrup to an acrylate copolymer.

10 The irradiation for both stages is preferably carried out in the absence of oxygen. Thus, it is normally carried out in a substantially inert atmosphere such as nitrogen, carbon dioxide, helium, argon, and the like. Air can also be excluded by
15 sandwiching the liquid polymerizable mixture between layers of solid sheet material and irradiating through the sheet material. As will be appreciated by those skilled in the art, such material can have low adhesion surfaces and can be removed after polymerization is
20 complete or one such surface can be a tape backing material. Preferably, the stages of irradiation are conducted continuously, or in-line without interruption of the polymerization process, i.e., the coated mixture is exposed to the first stage irradiation and then
25 immediately exposed to the second stage irradiation with no interruption of the inert atmosphere between the stages. Such a continuous process is presently thought to be desirable the lower the conversion effected in Stage 1 of the process.

30 Photoinitiators useful in the present invention include, but are not limited to, the benzoin ethers, substituted benzoin ethers such as benzoin methyl ether or benzoin isopropyl ether, substituted acetophenones such as 2,2-diethoxy-acetophenone, and 2,2-dimethoxy-2-
35 phenyl-acetophenone, substituted alpha-ketals such as 2-methyl-2-hydroxypropiophenone, aromatic sulphonyl chlorides such as 2-naphthalene sulphonyl chloride, and

- 10 -

photoactive oximes such as 1-phenyl-1,2-propanedione-2-(O-ethoxycarbonyl) oxime, and the substituted triazines. Preferably, the photoinitiator is present in an amount of from about 0.01 part to about 5 parts, and most preferably, about 0.10 to 2 parts by weight, based upon 100 total parts by weight of monomer.

The photopolymerizable composition preferably contains a crosslinking agent to enhance the cohesive strength of the resulting adhesive or article. Useful crosslinking agents which also function as photoinitiators are the chromophore-substituted halomethyl-s-triazines disclosed in U.S. Patent Nos. 4,330,590 and 4,329,384. Other suitable crosslinking agents include hydrogen abstracting carbonyls such as anthraquinone and benzophenone and their derivatives, as disclosed in U.S. 4,181,752, and polyfunctional acrylates such as 1,6-hexanedioldiacrylate, trimethylolpropane triacrylate and 1,2-ethylene glycol diacrylate, as well as those disclosed in U.S. Patent No. 4,379,201.

Where a foam-like material or foam psa adhesive tape is desirable, a monomer blend comprising microbubbles may be used. The microbubbles may be glass or they may be polymeric. The microbubbles should have an average diameter of 10 to 200 micrometers, and comprise from about 5 to about 65 volume percent of the pressure-sensitive adhesive layer. Preferred glass microspheres have average diameters of about 50 micrometers. Especially preferred microspheres are polymeric microspheres, such as those disclosed in U.S. Pat. Nos. 3,615,972, 4,075,238, and 4,287,308.

The adhesives and psa tapes made by utilizing the processes of this invention may include cellular pressure-sensitive adhesive membranes as discussed in U.S. 4,415,615.

- 11 -

A foam-like or cellular psa membrane can be made by the process of the present invention. Typical psa thickness may range from .3 to 4 mm.

Other materials which can be blended with the
5 polymerizable monomer mixture include fillers, tackifiers, foaming agents, antioxidants, plasticizers, reinforcing agents, dyes, pigments, fibers, fire retardants, and viscosity adjusting agents.

An especially useful filler material is
10 hydrophobic silica as disclosed in U.S. Pat. Nos. 4,710,536 and 4,749,590. In one preferred embodiment of the present invention, the pressure-sensitive adhesive layer further comprises from about 2 to about 15 parts per hundred parts (phr) of a hydrophobic
15 silica having a surface area of at least 10 m²/g.

The extent of polymerization can be monitored by measuring the refractive index of the adhesive layer. Refractive index is a sensitive measure of the extent of polymerization and for these systems changes from
20 about 1.4300 at the syrup stage to about 1.4700 at 100% reaction. The change in refractive index occurs linearly with conversion of acrylate unsaturation. This method is commonly applied in polymerization kinetics work. See, for example, discussions about the
25 method in *Polymerization at Advanced Degrees of Conversion*, G. P. Gladyshev and K. M. Gibov, Keter Press, Jerusalem, 1970.

The subsequent irradiation of Stage 2 is carried out at 280 to 500 nm wavelength and at a higher average
30 intensity (as compared to the first stage irradiation step) within the range of greater than 20 mW/cm²; preferably in the range of greater than 20 up to about 200 mW/cm²; and most preferably in the range of about 50 mW/cm² to 150 mW/cm². During the second stage
35 irradiation, the copolymerization reaction is at least substantially completed (i.e. preferably at least about

- 12 -

95 weight % monomer conversion has been achieved as well as any crosslinking) thereby forming the acrylic copolymer. In some instances it is desirable to cool the adhesive coated web during both stages of irradiation, and especially during the second stage irradiation. This can be done, for example, by pulling the adhesive coated film over a cooling plate, by blowing cooled nitrogen on the web, or by blowing cooled air onto the aforementioned sandwich constructions. Cooling of the adhesive coated web during Stage 2 becomes more desirable the greater the conversion effected in Stage 2. Absence of cooling may result in evaporation of monomer thereby resulting in an undesired change in the monomer composition in the resulting acrylic polymer.

The first stage of the irradiation uses low average intensity light ($0.1-20 \text{ mW/cm}^2$) obtained from, but not limited to, fluorescent black lamps. The type of lamps that are useful in the practice of the invention depend upon the photoinitiator that is used. The lamps should emit radiation at wavelengths needed to activate the photoinitiator. For example, fluorescent black lamps having an output between 280-500 nm are useful. For convenience, fluorescent black lamps having an output between 300-400 nm are preferred. The subsequent polymerization step, utilizes an average light intensity of greater than 20 mW/cm^2 obtained from high pressure or medium pressure mercury, mercury xenon, or similar type doped lamps which operate at 100-600 watts/inch input power. Intensities of up to about 200 mW/cm^2 are feasible with the state of the art lamps. Higher intensities may be possible as advancements in bulb technology are made.

Each stage of irradiation can further include zones of varying intensities within the ranges specified, i.e., the first stage irradiation can

- 13 -

include zones having varying low average intensity light, and the second stage can include zones having average light intensities greater than 20 mW/cm².

In addition to conducting the second stage
5 polymerization with high intensity electromagnetic radiation, it is also feasible to utilize high energy particulate matter such as, for example, electron beams.

Utilizing the process of this invention
10 substantial increases in processing speeds can be obtained while maintaining high performance psa properties.

The following non-limiting examples further illustrate the present invention. The test procedures
15 used for evaluating the tapes of the Examples are given below.

TEST PROCEDURES

180° Peel

20 A sample is prepared by cutting an adhesive-coated polyethylene terephthalate film into a strip 2.54 cm by 15.2 cm. The strip is then laminated to a smooth stainless steel panel and rolled down with 2 passes of a 2.04 kg. hard rubber covered roller. The sample is
25 left at room temperature for 15 minutes. The tape is then pulled away from the stainless steel panel at an angle of 180 degrees and a speed of 30.5 cm per minute on a tensile tester. Results are reported in Newtons/dm.

30

Static Shear

A sample is prepared by attaching a 2.54 cm wide by 15.2 cm long adhesive coated polyethylene terephthalate film strip to a smooth stainless steel
35 panel that has been cleaned with heptane. The adhesive coated strip is overlapped onto the panel a distance of 2.54 cm so that the total contact area of the adhesive

- 14 -

coated film on the stainless steel panel is 2.54 cm by 2.54 cm. The overlapped area is then rolled down with two passes of a 2.04 kg hard rubber covered roller. The panel is left at room temperature for 30 minutes.

- 5 For room temperature shear (RT), the panel is hung two degrees from the vertical plane to prevent peeling of the sample from the plate, and the free-hanging end of the adhesive coated strip is formed into a loop. A 500 or 1,000 gram weight is hung from the loop and a
- 10 timer is started. The Static Shear Value is recorded in minutes. If no failure occurs after 10,000 minutes, the test is stopped.

- If samples pass the room temperature static shear test, an elevated temperature test may be run. The
- 15 panel is hung at two degrees from the vertical in an air circulating oven (that has been preheated to 70°C) for 10 minutes to allow the sample to come up to temperature. A 500 or 1,000 gram weight is then hung on the loop and a timer is started. The Static Shear
- 20 Value is recorded in minutes and the test is stopped if no failure occurs after 10,000 minutes.

T-Peel

- A double coated tape sample is placed between two
- 25 strips of 25 mm x 200 mm x 0.125 mm anodized aluminum, leaving an adhesive free 25 mm tab at each end of each aluminum strip. The assembly is rolled down with a 6.8 kg roller with one pass forward and one pass backward. The assembly is conditioned at room temperature for 1-2
- 30 hours. The tabs are bent back at 90° in opposite directions and respectively clamped in the upper and lower jaws of a tensile testing machine. The jaws are separated at 30 mm/minute. The force required to pull apart the tabs is recorded in Newtons/Decimeter (N/Dm).

- 35 The percentage (%) conversion is as described above using refractive index.

- 15 -

Example 1

A mixture of 90 parts of isooctyl acrylate (IOA), 10 parts of acrylic acid (AA) and 0.04 parts of Irgacure™ 651 photoinitiator (2,2-dimethoxy-2-phenyl acetophenone) was partially polymerized to a viscosity of about 3000 cps in a nitrogen atmosphere under ultraviolet radiation. To the partially polymerized mixture was added an additional 0.71 parts of Irgacure™ 651. The mixture was then knife coated to a thickness of 0.12 mm onto a 0.05 mm thick biaxially oriented poly(ethylene terephthalate) film and polymerized in a nitrogen atmosphere under a bank of fluorescent black light lamps (Sylvania F20T12BL) to a Stage 1 conversion of 42.4% using an average of 0.75 milliwatts/cm² of radiation for a total of 0.29 minutes. The energy from the lamps for the Stage 1 irradiation was measured with a Uvirad radiometer (Model No. UR365CH3) from E.I.T. (Electronic Instrumentation & Technology, Inc., Sterling, VA). The coated mixture was then exposed, without interruption of the inert environment, to a Stage 2 irradiation of an average of 109 mW/cm² of ultraviolet radiation (high intensity medium pressure mercury arc lamps set at 300 watts/inch) for 0.09 minutes to a conversion of over 95% to form a pressure sensitive adhesive. The intensity and energy from the lamps for the Stage 2 irradiation was measured with a Uvimap radiometer (Model No. UM365H-S) from E.I.T. The adhesive coated tape was tested for peel adhesion and static shear and the data is shown in Table 2. The test data shows that an acceptable pressure sensitive adhesive tape can be made as compared to 810 Magic™ Tape from Minnesota Mining & Manufacturing Company (Comparative Example C-1 in Table 3).

- 16 -

Examples 2-7

Pressure sensitive adhesives were prepared as in Example 1 except that various radiation intensities, and varying amounts of photoinitiator were added to the prepolymerized mixture to obtain varying Stage 1 conversions as shown below in Table 1. Stage 2 conversions are shown in Table 2 with test data for peel adhesion and static shear. The conversion after Stage 2 was greater than 95% in all cases. In all cases, acceptable pressure sensitive adhesive tapes were made.

Table 1

Example	Parts Irg. 651	Avg. UV Intensity, mW/cm ²	Stage 1 Exposure Time - min.	Stage 1 Conversion, %
2	0.14	1.5	0.83	77.1
3	0.50	0.75	0.53	70.3
4	0.75	0.75	0.44	58.0
5	0.75	0.75	0.36	49.2
6	1.00	0.75	0.17	39.5
7	1.00	0.75	0.17	39.5

- 17 -

Table 2

Example	Stage 2 - Average Intensi- ty, mW/cm ²	Stage 2 Exposur e Time- min	Total Exposur e Time- min	180°Pee l Adhesio n, N/dm	Static Shear** Minutes RT
1	109	0.09	0.38	56	84
2	118	0.09	0.91	36	572
3	109	0.08	0.61	30	1,012
4	109	0.09	0.53	39	302
5	109	0.09	0.45	46	179
6	118	0.21	0.38	101*	10,000+
7	118	0.13	0.30	45	63

*Failure was cohesive, i.e. the adhesive layer split;
all other samples failed adhesively between the
adhesive and the stainless steel panel.

**A 1,000 gram weight was used.

+Over 10,000 minutes.

Example 8

In this example an adhesive is prepared with a crosslinking agent to improve elevated temperature shear strength. A prepolymerized mixture was made as in Example 1. To this mixture was added an additional 0.71 parts of Irgacure™ 651 and 0.8 parts of 1,6-hexanediol diacrylate (HDDA) as a crosslinker. The mixture was coated and polymerized as described in Example 1 to a Stage 1 conversion of 42.4% and to a final conversion after Stage 2 of over 95% using an ultraviolet radiation average intensity of 109 mW/cm². The total reaction time of Stage 1 and Stage 2 was 0.38 min. Test results are shown in Table 3.

- 18 -

Example 9

A pressure sensitive adhesive was made as described in Example 8 except that a triazine crosslinker was used instead of HDDA. To the prepolymerized mixture of Example 1 was added 0.10 parts of Irgacure™ 651 and 0.1 parts 2,4-bistrichloromethyl -6-(3,4-dimethoxyphenyl)-s-triazine. The average UV radiation intensity for Stage 1 was 1.5 mW/cm² for 0.56 minute. Stage 2 conditions and test data are shown in Table 3.

Table 3

Example	Stage 2 Intensity, mW/cm ²	Stage 2 Exposure, Time-min	Total Exposure, Time-min	180° Peel Adhesion, N/dm	Static Shear* Minutes at 70°C
8	109	0.09	0.38	36	10,000+
9	70	0.07	0.63	41	10,000+
C-1	--	--	--	17	240

*A 500 gram weight was used.

Examples 10-12

Pressure sensitive adhesive mixtures were prepared as described in Example 1 except that 0.8 part of 1,6-hexanedioldiacrylate (HDDA) was added to each mixture. The mixtures were coated onto the release coated surface of a polyester film and the coated film was pulled over a cooling plate set at about 0°C in a chamber under a nitrogen atmosphere at the web speeds, in meters/min (m/min) shown in Table 4. The exposure times and intensities were those shown in Table 4. The Stage 1 average intensities were calculated from the energy measured with a Uvirad radiometer (from E.I.T.).

- 19 -

The Stage 2 intensities were measured with a Uvimap radiometer (from E.I.T.). The adhesives were tested for 180° peel adhesion and static shear performance, and the results are shown in Table 5.

Table 4

Example	Stage 1 average intensity mW/cm ²	Stage 1 Exposure Time-min.	Stage 1 Conversion &	Stage 2 Average Intensity mW/cm ²	Stage 2 Exposure Time-min.	Total Exposure Time-min	Web Speed m/min.
10	0.70	0.11	30	25.2	0.15	0.26	0.47
11	0.7	0.071	20	25.4	0.09	0.16	0.74
12	0.7	0.036	15	45.5	0.05	0.086	1.48

- 21 -

Table 5

Example	180° Peel N/dm	Static Shear - 1000 gram wt - min @ RT	Static Shear - 500 gram wt - min @ 70°C
10	48	5001	10,000+
11	49	2933	10,000+
12	43	345	10,000+

The test results in Table 5 show that Stage 1 conversions of 15% can be used to make acceptable pressure sensitive adhesives.

Example 13 and Comparative Example C-2

An adhesive mixture was prepared by mixing 87.5 parts of isooctyl acrylate and 12.5 parts of acrylic acid with 0.04 parts of 2,2-dimethoxy-2-phenyl acetophenone photoinitiator (Irgacure™ 651). The mixture was partially polymerized under UV lights in a nitrogen atmosphere to form a syrup having a viscosity of about 3000 cps (Brookfield). An additional 0.1 phr (parts per hundred syrup) of Irgacure™ 651 photoinitiator was added to the mixture along with 0.056 phr of hexanedioldiacrylate, 8 phr glass microbubbles (C15/250 glass microbubbles available from Minnesota Mining & Manufacturing Co.), and 10 phr fumed silica (Aerosil™ 972 available from DeGussa). The mixture was mixed with a propeller mixer for about 10 minutes and degassed in a desiccator using a vacuum pump. The mixture was then coated to a thickness of about 1 mm between two 0.05 mm thick biaxially oriented poly(ethylene terephthalate) films that had been coated

- 22 -

with a release coating, and irradiated according to the conditions shown in Table 6 according to the procedure described in Example 1. The resulting foam-like sheet was made into a double coated tape by laminating acrylic pressure sensitive adhesives to each side of the sheet and tested for T-peel. Results are shown in Table 6.

In Example C-2, the films sandwiching the adhesive were pulled through UV lights as described in the Stage 1 conversion of Example 1. The lamps were adjusted to provide zones of 3 different intensities as shown in Table 6. The time in each zone is also shown. Lamps were used only on the top side of the adhesive. The T-peel results are shown in Table 6.

In Example 13, the films were pulled through Stage 1 as described in Comparative Example C-2, except with 2 zones providing the intensities shown in Table 6. The Stage 2 conversion was conducted using the high intensity mercury arc lamps described in Example 1. The exposure times and intensities, and the T-peel test results are shown in Table 6.

Table 6

Example	Stage 1 Exposure			Stage 2 Exposure		Total Exposure Time-min	T-Peel Results N/Dm
	Zone 1 Average Intensity- Time mW/cm ² -min	Zone 2 Average Intensity- Time mW/cm ² -min	Zone 3 Average Intensity- Time mW/cm ² -min	Average Intensity mW/cm ²	Time min		
C-2	0.30-1.33	0.70-1.33	2.0-2.0	none	none	4.66	26
13	0.62-1.78	0.78-1.78	none	109.0	0.08	3.64	26

- 24 -

The results in Table 6 show that the total exposure time can be reduced about 22% by using a high intensity Stage 2 cure, without sacrificing T-peel performance.

- 5 Reasonable modifications and variations are possible from the foregoing disclosure without departing from either the spirit or the scope of the present invention as defined by the claims.

- 25 -

WE CLAIM:

1. A multi-stage irradiation process for the production of an acrylic-based composition comprising
5 the sequential steps of:
 - (a) forming a monomeric mixture or partially prepolymerized syrup comprising:
 - (i) about 50-100 parts by weight of at least one acrylic acid ester of an alkyl
10 alcohol, said alcohol containing from 1 to 14 carbon atoms;
 - (ii) about 0-50 parts by weight of at least one copolymerizable monomer; and
 - (iii) a photoinitiator;
 - 15 (b) irradiating the resulting monomeric mixture or partially prepolymerized syrup with electromagnetic radiation of from about 280 to 500 nanometers wavelength and from .01 to 20 milliwatts per centimeter squared (mW/cm²)
20 average light intensity to effect conversion of from about 5-70 weight % of said monomeric mixture or partially prepolymerized syrup to an acrylic copolymer; and
 - (c) thereafter, further irradiating the resulting
25 acrylic copolymer resulting from step (b) with electromagnetic radiation of from about 280 to 500 nm wavelength and having an average light intensity of greater than 20 mW/cm² to at least substantially complete the
30 polymerization reaction of said acrylic copolymer.
2. Process according to Claim 1 wherein said
weight % conversion effected in step (b) is about 5-50
35 weight %.

- 26 -

3. Process according to Claim 1 wherein said weight % conversion effected in step (b) is about 10-50 weight %.

5 4. Process according to Claim 1 wherein said weight % conversion effected in step (b) is about 10-40 weight %.

10 5. Process according to Claim 1 wherein said weight % conversion effected in step (b) is about 20-40 weight %.

15 6. Process according to Claim 1 wherein said at least one acrylic acid ester is an ester of a non-tertiary alcohol, said alcohol containing from 1 to 14 carbon atoms and said at least one copolymerizable monomer is an ethylenically unsaturated monomer.

20 7. Process according to Claim 1 wherein said at least one acrylic acid ester is selected from the group consisting of: 2-ethyl-hexyl acrylate, isooctyl acrylate, isononyl acrylate, and butyl acrylate.

25 8. Process according to Claim 1 wherein said at least one copolymerizable monomer is selected from the group consisting of: acrylic acid, methacrylic acid, acrylamide, acrylonitrile, methacrylonitrile, N-substituted acrylamides, hydroxyacrylates, N-vinyl pyrrolidone, N-vinyl caprolactam, maleic anhydride, 30 isobornyl acrylate, and itaconic acid.

9. Process according to Claim 1 wherein said photoinitiator is present in an amount of from about .01 to 5 parts by weight.

35

- 27 -

10. Process according to Claim 1 wherein said photoinitiator is present in an amount of from about .10 to 2 parts by weight.

5 11. Process according to Claim 1 wherein said monomeric mixture or prepolymerized syrup further comprises a crosslinking agent.

12. Process according to Claim 11 wherein the
10 crosslinking agent is a triazine, benzophenone, or a substituted benzophenone.

13. Process according to Claim 12 wherein the crosslinking agent is a trihalomethyl-s-triazine.
15

14. Process according to Claim 11 wherein the crosslinking agent is a multi-functional acrylate.

15. Process according to Claim 1 wherein said
20 average light intensity in step 1(c) is in the range of greater than 20 up to 200 mW/cm².

16. Process according to Claim 1 wherein said average light intensity in step 1(c) is in the range of
25 50 to 150 mW/cm².

17. Process according to Claim 1 wherein the acrylic-based reaction mixture is cooled during the irradiation steps in 1(b) and 1(c).
30

18. Process according to Claim 1 wherein the multi-stage irradiation process is continuous without interruption.

- 28 -

19. Process according to Claim 1 wherein the multi-stage irradiation process is conducted under inert conditions.

5 20. Process according to Claim 19 wherein the acrylic-based reaction mixtures in both the first and second stage irradiation processes are positioned between layers of solid sheet material which are transparent to electromagnetic radiation having a
10 wavelength in the range of 280 to 500 nm.

21. An adhesive made according to the process of Claim 1.

15 22. A multi-step irradiation process for the production of an acrylic-based pressure-sensitive adhesive tape comprising the sequential steps of:

- 20 (a) coating onto at least one side of a suitable substrate a photopolymerizable, monomeric mixture or partially prepolymerized syrup comprising:
- 25 (i) about 50-100 parts by weight of at least one acrylic acid ester of an alkyl alcohol, said alcohol containing from 1 to 14 carbon atoms;
- (ii) about 0-50 parts by weight of at least one copolymerizable monomer; and
- (iii) a photoinitiator;
- 30 (b) irradiating the resulting coated substrate with electromagnetic radiation of from about 280 to 500 nanometers wavelength and from .01 to 20 milliwatts per centimeter squared (mW/cm^2) average light intensity to effect about 5-70 weight % conversion of said
- 35 monomeric mixture or partially prepolymerized syrup to an acrylic copolymer; and

- 29 -

(c) thereafter, irradiating the partially polymerized coated substrate resulting from step (b) with electromagnetic radiation of from about 280 to 500 nm wavelength and having an average light intensity of greater than 20 mW/cm² to at least substantially complete the polymerization reaction of said acrylic copolymer.

23. Process according to Claim 22 wherein said weight % conversion effected in step (b) is about 5-50 weight %.

24. Process according to Claim 22 wherein said weight % conversion effected in step (b) is about 10-40 weight %.

25. Process according to Claim 22 wherein said average light intensity in step (c) is in the range of greater than 20 up to 200 mW/cm².

26. Process according to Claim 22 wherein said average light intensity in step (c) is in the range of 50 to 150 mW/cm².

27. A pressure-sensitive adhesive tape made according to the process of Claim 22.

28. A multi-stage irradiation process for the production of an acrylic-based composition comprising the sequential steps of:

(a) forming a monomeric mixture or partially prepolymerized syrup comprising:

(i) about 50-100 parts by weight of at least one acrylic acid ester of an alkyl

- 30 -

alcohol, said alcohol containing from 1 to 14 carbon atoms;

(ii) about 0-50 parts by weight of at least one copolymerizable monomer; and

(iii) a photoinitiator;

5 (b) irradiating the resulting monomeric mixture or partially prepolymerized syrup in a substantially inert environment with electromagnetic radiation of from about 280
10 to 500 nanometers wavelength and from .01 to 20 milliwatts per centimeter squared (mW/cm^2) average light intensity to effect conversion of from about 5-85 weight % of said monomeric mixture or partially prepolymerized syrup to
15 an acrylic copolymer; and

(c) thereafter and while maintaining the substantially inert environment, further
irradiating the resulting acrylic copolymer
20 resulting from step (b) with electromagnetic radiation of from about 280 to 500 nm wavelength and having an average light intensity of greater than $20 \text{ mW}/\text{cm}^2$ to at
least substantially complete the
polymerization reaction of said acrylic
25 copolymer.

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : C09J 4/00, C08F 2/48	A3	(11) International Publication Number: WO 92/15394 (43) International Publication Date: 17 September 1992 (17.09.92)
(21) International Application Number: PCT/US92/01626 (22) International Filing Date: 28 February 1992 (28.02.92) (30) Priority data: 662,122 28 February 1991 (28.02.91) US 820,057 16 January 1992 (16.01.92) US (71) Applicant: MINNESOTA MINING AND MANUFACTURING COMPANY [US/US]; 3M Center, P.O. Box 33427, Saint Paul, MN 55133 (US). (72) Inventors: MOON, John, D. ; ZIEGLER, Louis, A. ; VESLEY, George, F. ; MEHNER, Robert, C. ; EDBERG, Mark, S. ; ANDERSON, Robert, D. ; P.O. Box 33427, Saint Paul, MN 55133 (US).		(74) Agents: SPRAGUE, Robert, W. et al.; Office of Intellectual Property Counsel, Minnesota Mining and Manufacturing Company, P.O. Box 33427, Saint Paul, MN 55133 (US). (81) Designated States: AT (European patent), AU, BE (European patent), BR, CA, CH (European patent), DE (European patent), DK (European patent), ES (European patent), FR (European patent), GB (European patent), GR (European patent), IT (European patent), JP, KR, LU (European patent), MC (European patent), NL (European patent), SE (European patent). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i> (88) Date of publication of the international search report: 29 October 1992 (29.10.92)
(54) Title: MULTI-STAGE IRRADIATION PROCESS FOR PRODUCTION OF ACRYLIC BASED COMPOSITIONS AND COMPOSITIONS MADE THEREBY (57) Abstract Disclosed is a novel, multi-stage irradiation process for the production of acrylic-based compositions such as adhesives or pressure-sensitive adhesive tapes. The first irradiation step or stage employs electromagnetic radiation at a relatively low average intensity (i.e., 0.1 to 20 mW/cm ²) to effect a relatively low extent of monomer conversion, and the subsequent step employs electromagnetic radiation at a relatively higher average intensity (i.e., greater than 20 mW/cm ²) to complete the photopolymerization. Also disclosed are acrylic-based psa tape materials made by the novel process.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.


AT	Austria	FI	Finland	MI	Mali
AU	Australia	FR	France	MN	Mongolia
BB	Barbados	GA	Gabon	MR	Mauritania
BE	Belgium	GB	United Kingdom	MW	Malawi
BF	Burkina Faso	GN	Guinea	NL	Netherlands
BG	Bulgaria	GR	Greece	NO	Norway
BJ	Benin	HU	Hungary	PL	Poland
BR	Brazil	IE	Ireland	RO	Romania
CA	Canada	IT	Italy	RU	Russian Federation
CF	Central African Republic	JP	Japan	SD	Sudan
CG	Congo	KP	Democratic People's Republic of Korea	SE	Sweden
CH	Switzerland	KR	Republic of Korea	SN	Senegal
CI	Côte d'Ivoire	LI	Liechtenstein	SU	Soviet Union
CM	Cameroon	LK	Sri Lanka	TD	Chad
CS	Czechoslovakia	LU	Luxembourg	TC	Togo
DE	Germany	MC	Monaco	US	United States of America
DK	Denmark	MG	Madagascar		
ES	Spain				

INTERNATIONAL SEARCH REPORT

PCT/US 92/01626

International Application No

I. CLASSIFICATION OF SUBJECT MATTER (If several classification symbols apply, indicate all) ⁶		
According to International Patent Classification (IPC) or to both National Classification and IPC		
Int.Cl. 5 C09J4/00; C08F2/48		
II. FIELDS SEARCHED		
Minimum Documentation Searched ⁷		
Classification System	Classification Symbols	
Int.Cl. 5	C09J ; C08F	
Documentation Searched other than Minimum Documentation to the extent that such Documents are included in the Fields Searched ⁸		
III. DOCUMENTS CONSIDERED TO BE RELEVANT⁹		
Category ⁹	Citation of Document, ¹¹ with indication, where appropriate, of the relevant passages ¹²	Relevant to Claim No. ¹³
X	FR,A,2 596 765 (DAI-ICHI KOGYO SEIYAKU) 9 October 1987 see page 5, line 23 - page 6, line 34 see page 11, line 13 - page 12, line 24 ---	1-6, 8-10, 18, 19, 28
A	US,A,4 181 752 (MARTENS ET AL.) 1 January 1980 cited in the application see the whole document ---	1-28
A	GB,A,1 241 823 (SUN CHEMICAL CORPORATION) 4 August 1971 see page 3, column 2, line 67 - line 79 see page 5, column 2, line 80 - page 6, column 1, line 32 ---	1, 22, 28

-/--		
<p>⁹ Special categories of cited documents: ¹⁰</p> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.</p> <p>"A" document member of the same patent family</p>		
IV. CERTIFICATION		
Date of the Actual Completion of the International Search	Date of Mailing of this International Search Report	
16 SEPTEMBER 1992	29. 09. 92	
International Searching Authority	Signature of Authorized Officer	
EUROPEAN PATENT OFFICE	ANDRIOLLO G.R. 	

III. DOCUMENTS CONSIDERED TO BE RELEVANT (CONTINUED FROM THE SECOND SHEET)		
Category *	Citation of Document, with indication, where appropriate, of the relevant passages	Relevant to Claims No.
A	US, A, 4 329 384 (VESLEY ET AL.) 11 May 1982 cited in the application ---	1, 11-13, 21, 22, 27, 28

ANNEX TO THE INTERNATIONAL SEARCH REPORT ON INTERNATIONAL PATENT APPLICATION NO.

US 9201626
SA 58107

This annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information. 16/09/92

Patent document cited in search report	Publication date	Patent family member(s)	Publication date	
FR-A-2596765	09-10-87	JP-A-	62235305	15-10-87
		DE-A-	3706852	08-10-87
		GB-A, B	2189792	04-11-87
		US-A-	4762862	09-08-88

US-A-4181752	01-01-80	None		

GB-A-1241823	04-08-71	CH-A-	542888	30-11-73
		DE-A-	1770825	19-06-75
		DE-A-	1694930	21-10-71
		GB-A-	1198259	08-07-70
		GB-A-	1241824	04-08-71
		US-A-	3551235	29-12-70
		US-A-	3551246	29-12-70
		US-A-	3551311	29-12-70
		US-A-	3552986	05-01-71
		US-A-	3558387	26-01-71

US-A-4329384	11-05-82	AU-B-	537310	14-06-84
		AU-A-	6780481	31-08-81
		CA-A-	1145294	26-04-83
		DE-A-	3105342	17-12-81
		EP-A, B	0045769	17-02-82
		WO-A-	8102261	20-08-81
